

Circle Silk Premium White

Papier powlekany bezdrzewny, recyclingowy.

Dane techniczne

Gramatura / Weight (g/m ²)	ISO 536	90	100	115	130	150	170	200	250	300	350
Grubość / Thickness (µm)	ISO 534	70	77	88	100	115	134	162	207	261	315
Spulchnienie / Bulk (cm ³ /g)	ISO 534	0.78	0.77	0.77	0.77	0.77	0.79	0.81	0.83	0.87	0.9
Gładkość / Smoothness Bekk (s)	ISO 5627	500	500	500	450	400	350	300	200	150	100
Połysk / Gloss Gardner (%)	ISO 8254-1	40 max	40 max	45 max	45 max	45 max	45 max	45 max	45 max	45 max	45 max
Jasność / Whiteness CIE (%)	ISO 11475	120	120	120	120	120	121	121	121	121	121
Jasność / Brightness ISO (%)	ISO 2470 (D65)	96	96	96	96	96	96	96	96	96	96
Nieprzeźroczystość / Opacity (%)	ISO 2471	92.5	94	95	96	97 min	98 min	98 min	98 min	98 min	98 min